

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
22 May 2003 (22.05.2003)

PCT

(10) International Publication Number  
**WO 03/041685 A1**

(51) International Patent Classification<sup>7</sup>: **A61K 9/00, 47/34**

(21) International Application Number: **PCT/US02/36717**

(22) International Filing Date:  
14 November 2002 (14.11.2002)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
60/336,254 14 November 2001 (14.11.2001) US

(71) Applicant: **ALZA CORPORATION** [US/US]; 1900  
Charleston Road, P.O. Box 7210, Mountain View, CA  
94039-7210 (US).

(72) Inventors: **CHEN, Guohua**; 399 Sunset Avenue, Sun-  
nyvale, CA 94086 (US). **HOUSTON, Paul, Ricky**; 3889  
Blackstone Court, Hayward, CA 94542 (US). **WRIGHT,**  
**Jeremy, Corwin**; 631 Cuesta Drive, Los Altos, CA 94024-

41155 (US). **FRANSSON, Jonas**; Sloydgatan 4, S-752 38  
Uppsala (SE). **HGERTMAN, Birger**; Svardsliljevagen 86,  
S-165 77 Hasselby (SE).


(74) Agents: **DATE, Vandana et al.**; ALZA CORPORATION,  
1900 Charleston Road, P.O. Box 7210,, Mountain View,  
CA 94039-7210 (US).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,  
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,  
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,  
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,  
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,  
MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG,  
SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VN,  
YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM,  
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),  
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),  
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,  
ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SK,  
TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,  
GW, ML, MR, NE, SN, TD, TG).

[Continued on next page]

(54) Title: INJECTABLE DEPOT COMPOSITION



(57) Abstract: Gel compositions are provided that can be utilized as carriers for beneficial agents when injected into a subject and which can provide sustained release of the beneficial agent over time. In particular, gel compositions containing an agent that renders the composition thixotropic to facilitate injection of the gel into a subject with minimal discomfort to the subject are described.

WO 03/041685 A1

**Published:**

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

*For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

## INJECTABLE DEPOT COMPOSITION

## CROSS-REFERENCE RELATED TO APPLICATION

[0001] This application claims the benefit of U.S. Provisional Application  
5 No. 60/336,254, filed on November 14, 2001.

## BACKGROUND OF THE INVENTION

## Field of the Invention

[0002] The present invention relates generally to gel compositions that can  
10 be utilized as carriers for beneficial agents when injected into a subject and  
which can provide sustained release of the beneficial agent over time. More  
particularly, it relates to gel compositions such as described above that  
contain an agent that renders the composition thixotropic to facilitate injection  
of the gel into a subject with minimal discomfort to the subject.

15

## Description of the Related Art

[0003] Biodegradable polymers have been used for many years in medical  
applications. The majority of these biodegradable polymers have been based  
upon glycolide, lactide, caprolactone, and copolymers thereof. Within the last  
20 decade, greater emphasis has been placed on the use of injectable polymer  
compositions that provide a depot of beneficial agent for dispensing to a  
subject over time.

[0004] One way to avoid the incision needed to implant drug delivery  
systems is to inject them as small particles, microspheres, or microcapsules.  
25 For example, U.S. Patent No. 5,019,400 describes the preparation of  
controlled release microspheres via a very low temperature casting process.  
These materials may or may not contain a drug which can be released into  
the body. Although these materials can be injected into the body with a  
syringe, they do not always satisfy the demand for a biodegradable implant.

30 [0005] Because they are particulate in nature, they do not form a  
continuous film or solid implant with the structural integrity needed for certain  
prostheses. When inserted into certain body cavities such as a mouth, a

periodontal pocket, the eye, or the vagina where there is considerable fluid flow, these small particles, microspheres, or microcapsules are poorly retained because of their small size and discontinuous nature. Further, the particles tend to aggregate and thus their behavior is hard to predict. In addition, microspheres or microcapsules prepared from these polymers and containing drugs for release into the body are sometimes difficult to produce on a large scale, and their storage and injection characteristics present problems. Furthermore, one other major limitation of the microcapsule or small-particle system is their lack of reversibility without extensive surgical intervention. That is, if there are complications after they have been injected, it is considerably more difficult to remove them from the body than with solid implants. A still further limitation on microparticles or microcapsulation is the difficulty in encapsulating protein and DNA-based drugs without degradation caused by solvents and temperature extremes.

15 [0006] The art has developed various drug delivery systems in response to the aforementioned challenges. For instance, U.S. Patent No. 4,938,763 and its divisional U.S. Patent No. 5,278,201 relate to a biodegradable polymer for use in providing syringeable, in-situ forming, solid biodegradable implants for animals. In one embodiment, a thermoplastic system is used wherein a non-  
20 reactive polymer is dissolved in a biocompatible solvent to form a liquid which is placed in the animal wherein the solvent dissipates to produce the solid implant. Alternatively, a thermosetting system is used wherein effective amounts of a liquid acrylic ester-terminated, biodegradable prepolymer and a curing agent are formed and the liquid mixture is placed within the animal  
25 wherein the prepolymer cures to form the solid implant. It is stated that the systems provide a syringeable, solid biodegradable delivery system by the addition of an effective level of a biologically active agent to the liquid before the injection into the animal.

### 30 BRIEF SUMMARY OF THE INVENTION

[0007] Gel compositions are provided that can be utilized as carriers for beneficial agents when injected into a subject and which can provide sustained release of the beneficial agent over time. In particular, the

compositions containing an agent that renders the composition thixotropic to facilitate injection of the gel into a subject with minimal discomfort to the subject are described.

[0008] U.S. Patent No. 5,242,910 describes a sustained release  
5 composition for treating periodontal disease. The composition comprises copolymers of lactide and glycolide, triacetin (as a solvent/plasticizer) and an agent providing relief of oral cavity diseases. The composition can take the form of a gel and can be inserted into a periodontal cavity via a syringe using  
10 either a needle or a catheter. As additional optional components, the composition can contain surfactants, flavoring agents, viscosity controlling agents, complexing agents, antioxidants, other polymers, gums, waxes/oils, and coloring agents. One illustrative viscosity controlling agent set forth in one of the examples is polyethylene glycol 400. U.S. Patent Nos. 5,620,700 and 5,556,905 relate to polymer compositions for injectable implants using  
15 solvents and/or plasticizers.

[0009] Prior art polymer compositions for injectable implants have used solvent/plasticizers that are very or relatively soluble in aqueous body fluids to promote rapid solidification of the polymer at the implant site and promote diffusion of drug from the implant. However, it has now been observed that a  
20 serious problem associated with prior art polymeric implants utilizing water soluble polymer solvents is the rapid migration of water into the polymer composition when the implant is placed in the body and exposed to aqueous body fluids. This characteristic often results in uncontrolled release of beneficial agent that is manifested by an initial, rapid release of beneficial  
25 agent from the polymer composition, corresponding to a "burst" of beneficial agent being released from the implant. The burst often results in a substantial portion of the beneficial agent, if not all, being released in a very short time, e.g., hours or 1-2 days. Such an effect can be unacceptable, particularly in those circumstances where sustained delivery is desired, i.e., delivery of  
30 beneficial agent over a period of a week or a month or more, or where there is a narrow therapeutic window and release of excess beneficial agent can result in adverse consequences to the subject being treated, or where it is

necessary to mimic the naturally-occurring daily profile of beneficial agents, such as hormones and the like, in the body of the subject being treated.

**[00010]** In an attempt to control burst and modulate and stabilize the delivery of the beneficial agent the prior art has coated particles of beneficial agent to retard release into an aqueous environment and extend release of the beneficial agent over time. Alternatively, various stabilizing or release modulating agents, such as metal salts as described in U.S. Patents 5,656,297, 5,654,010, 4,985,404 and 4,853,218 have been used. U.S. Patent No. 3,923,939 describes a method of reducing initial burst of an active agent from a delivery device by removing, prior to implantation, active agent from the exterior surface of the delivery device and through a layer of at least 5% of the overall body thickness extending from the exterior surface of the device.

**[00011]** Notwithstanding some success, those methods have not been entirely satisfactory for the large number of beneficial agents that would be effectively delivered by implants, since in many instances the modulation and stabilization effect is the result of the formation of a complex of the metal ion with the beneficial agent. When such complexes do not form, the stabilization/modulation effect may not be adequate to prevent undesirable "burst" of the beneficial agent upon its introduction into the implant site.

**[00012]** U.S. Patent No. 6,130,200 describes a viscous gel carrier for a beneficial agent that can be injected into a subject. Use of a viscous gel lowers the initial burst of beneficial agent that is often seen with injectable depot systems. Notwithstanding the many advantages of the system described in the patent, in certain applications the viscosity of the gel may be so high as to result in relatively high injection forces required to dispense the gel from a syringe.

**[00013]** International application WO 98/27962 describes the formation of a thixotropic gel composition that provides for shear thinning and maintains acceptable injectability of the gel such that lower injection forces are needed

to expel the gel from a syringe and also lower the likelihood of substantial discomfort to a subject by use of smaller needles than would otherwise be required. While the systems described therein provide suitable depot systems for many applications, the described system utilized relatively large amounts of emulsifying agent, e.g., about one-third of the total weight of the composition. It has been discovered that in certain systems smaller quantities of certain compounds may be mixed with lactic acid-based polymers and a suitable solvent for the polymer that modify the flow characteristics of the gel formed, without the formation of an emulsion but still resulting in thixotropic compositions that are readily injectable through needles having a gauge that when used is not unduly uncomfortable to a subject. Also, use of such smaller amounts of an agent that imparts thixotropic properties to the gel may allow for smaller depot volume and mass without diminishing delivery of a required amount of beneficial agent over a prolonged period of time for an intended therapeutic effect.

#### SUMMARY OF THE INVENTION

**[00014]** In one aspect the invention comprises a composition comprising a lactic acid-based polymer, a solvent that forms a polymer solution with said polymer, and an amount of an agent mixed with the polymer solution effective to form a thixotropic composition, said agent being selected from the group consisting essentially of lower alkanols and said amount being less than 15 weight percent of the combined weight of the solvent and the agent. The lower alkanols are straight or branched chain alcohols having 2-6 carbon atoms as exemplified by ethanol, propanol, isopropanol and the like. A preferred agent is ethanol. The composition may include an amount of ethanol that is greater than or equal to 0.01 weight percent and less than or equal to 15 weight percent of the combined weight of the solvent and the agent. The composition may include an amount of ethanol that is greater than or equal to 0.1 weight percent and less than or equal to 5 weight percent of the combined weight of the solvent and the agent. The composition may include an amount of ethanol that is greater than or equal to 0.5 weight percent and less than or equal to 5 weight percent of the combined weight of the solvent and the agent.

**[00015]** In another aspect, the invention comprises a composition comprising polylactic acid polymer, a solvent that forms a polymer solution with said polymer, and an amount of an agent mixed with the polymer solution effective to form a thixotropic composition, said agent being selected from the group consisting essentially of lower alkanols and said amount being less than 15 weight percent of the combined weight of the solvent and the agent. The lower alkanols are straight or branched chain alcohols having 2-6 carbon atoms as exemplified by ethanol, propanol, isopropanol and the like. A preferred agent is ethanol. The composition may include an amount of ethanol that is greater than or equal to 0.01 weight percent and less than or equal to 15 weight percent of the combined weight of the solvent and the agent. The composition may include an amount of ethanol that is greater than or equal to 0.1 weight percent and less than or equal to 5 weight percent of the combined weight of the solvent and the agent. The composition may include an amount of ethanol that is greater than or equal to 0.5 weight percent and less than or equal to 5 weight percent of the combined weight of the solvent and the agent. The polylactic acid polymer may have a weight average molecular weight in the range of about 1,000 to about 120,000; preferably about 5,000 to about 50,000; and more preferably about 8,000 to about 30,000.

**[00016]** In yet another aspect, the invention comprises a composition comprising a lactic acid-based polymer formed as a copolymer of lactic acid and glycolic acid, a solvent that forms a polymer solution with said polymer, and an amount of an agent mixed with the polymer solution effective to form a thixotropic composition, said agent being selected from the group consisting essentially of lower alkanols and said amount being less than 15 weight percent of the combined weight of the solvent and the agent. The lower alkanols are straight or branched chain alcohols having 2-6 carbon atoms as exemplified by ethanol, propanol, isopropanol and the like. A preferred agent is ethanol. The composition may include an amount of ethanol that is greater than or equal to 0.01 weight percent and less than or equal to 15 weight percent of the combined weight of the solvent and the agent. The composition may include an amount of ethanol that is greater than or equal to 0.1 weight percent and less than or equal to 5 weight percent of the combined weight of the solvent and the agent. The composition may include an amount of ethanol that is greater than or equal to 0.5 weight percent and less than or equal to 5 weight percent of the combined weight of the solvent and the agent. The polylactic acid polymer may have a weight average molecular weight in the range of about 1,000 to about 120,000; preferably about 5,000 to about 50,000; and more preferably about 8,000 to about 30,000.



0.1 weight percent and less than or equal to 5 weight percent of the combined weight of the solvent and the agent. The composition may include an amount of ethanol that is greater than or equal to 0.5 weight percent and less than or equal to 5 weight percent of the combined weight of the solvent and the agent. The weight average molecular weight of the copolymer may be in the range of 1,000 to about 120,000; preferably about 5,000 to about 50,000; and more preferably about 8,000 to about 30,000.

**[00017]** In another aspect, the invention comprises a method of administering, locally or systemically, a beneficial agent to a subject which comprises implanting beneath the subject's body surface a composition as described above. Preferably, the system releases 40% or less by weight of the beneficial agent present in the viscous gel within the first 24 hours after implantation in the subject. More preferably, 30% or less by weight of the beneficial agent will be released within the first 24 hours after implantation, and the implanted composition has a burst index of 12 or less, preferably 8 or less.

**[00018]** In another aspect, the invention pertains to a composition and a method of administering such composition as described above, wherein the beneficial agent is selected from a drug, proteins, enzymes, hormones, polynucleotides, nucleoproteins, polysaccharides, glycoproteins, lipoproteins, polypeptides, steroids, analgesics, local anesthetics, antibiotic agents, chemotherapeutic agents, immunosuppressive agents, anti-inflammatory agents, antiproliferative agents, antimitotic agents, angiogenic agents, anticoagulants, fibrinolytic agents, growth factors, antibodies, ocular drugs, and metabolites, analogs, derivatives, fragments, and purified, isolated, recombinant and chemically synthesized versions of these species. In preferred embodiments, the beneficial agent is human growth hormone, methionine-human growth hormone; des-phenylalanine human growth hormone, alpha-, beta- or gamma-interferon, erythropoietin, glugacon, calcitonin, heparin, interleukin-1, interleukin-2, Factor VIII, Factor IX, luteinizing hormone, relaxin, follicle-stimulating hormone, atrial natriuretic factor, filgrastim epidermal growth factors (EGFs), platelet-derived growth

factor (PDGFs), insulin-like growth factors (IGFs), fibroblast-growth factors (FGFs), transforming-growth factors (TGFs), interleukins (ILs), colony-stimulating factors (CSFs, MCFs, GCSFs, GMCSFs), Interferons (IFNs), endothelial growth factors (VEGF, EGFs), erythropoietins (EPOs),

5 angiopoietins (ANGs), placenta-derived growth factors (PIGFs), and hypoxia induced transcriptional regulators (HIFs). Preferably, the beneficial agent is present in an amount of from 0.1 to 50% by weight of the combined amounts of the polymer, the solvent and the beneficial agent. In preferred

10 embodiments, the beneficial agent is in the form of particles dispersed or dissolved in the viscous gel, wherein the beneficial agent is in the form of particles having an average particle size of from 0.1 to 250 microns. In certain preferred embodiments, the beneficial agent is in the form of particles wherein the particle further comprises a component selected from the group consisting of a stabilizing agent, bulking agent, chelating agent and a

15 buffering agent.

#### BRIEF DESCRIPTION OF THE DRAWINGS

[00019] The foregoing and other objects, features and advantages of the present invention will be more readily understood upon reading the following

20 detailed description in conjunction with the drawings in which:

[00020] Figure 1 is a graph illustrating the relationship of viscosity and shear rate for various compositions of the present invention as compared to a prior art composition (formulations 1-4);

[00021] Figure 2 is a graph illustrating the relationship of viscosity and shear

25 rate for various compositions of the present invention as compared to a prior art composition (formulations 5-8);

[00022] Figure 3 is a graph illustrating the relationship between force required to inject compositions of the present invention (formulations 1-4) from a syringe using a 20 gauge needle and the percentage of ethanol in the

30 polymer solvent;

[00023] Figures 4A and 4B are graphs illustrating the relationship between force required to inject compositions of the present invention (formulations 9-16) from a syringe using a 24 gauge needle and the percentage of ethanol in the polymer solvent;

- 5 [00024] Figure 5 is a graph illustrating the in vivo release profile of human growth hormone obtained from various depot formulations, including those of the present invention (formulations 5-8);

- [00025] Figures 6A and 6B are graphs illustrating the in vivo release profile of human growth hormone obtained from various depot formulations, including  
10 those of the present invention (formulations 9-16);

[00026] Figure 7 shows the burst index profile profiling the release of human growth hormone ("hGH") from formulations 5-8 observed in rats; and

- [00027] Figure 8 shows the burst index profile profiling the release of human  
15 growth hormone ("hGH") from formulations 6 and 7 and the Neutropin® depot formulation observed in rats.

## DETAILED DESCRIPTION OF THE INVENTION

### Overview and Definitions:

- 20 [00028] The present invention is directed to gel compositions that can be utilized as carriers for beneficial agents when injected into a subject and which can provide sustained release of the beneficial agent over time. In particular, the invention is directed to gel compositions such as described above that contain an agent that renders the composition thixotropic to  
25 facilitate injection of the gel into a subject with minimal discomfort to the subject.

[00029] In describing and claiming the present invention, the following terminology will be used in accordance with the definitions set out below.

[00030] The singular forms "a," "an" and "the" include plural referents unless the context clearly dictates otherwise. Thus, for example, reference to "a solvent" includes a single solvent as well as a mixture of two or more different solvents, reference to "a beneficial agent" includes a single beneficial agent as well as two or more different beneficial agents in combination, reference to "an alcohol" includes a single alcohol as well as a mixture of two or more different alcohols, and the like.

[00031] The term "beneficial agent" means an agent that effects a desired beneficial, often pharmacological, effect upon administration to a human or an animal, whether alone or in combination with other pharmaceutical excipients or inert ingredients.

[00032] As used herein, the term "polynucleotide" refers to a polymeric form of nucleotides of any length, either ribonucleotides or deoxyribonucleotides, and includes double- and single-stranded DNA and RNA. It also includes known types of modifications, substitutions, and internucleotide modifications, which are known in the art.

[00033] As used herein, the term "recombinant polynucleotide" refers to a polynucleotide of genomic, cDNA, semisynthetic, or synthetic origin which, by virtue of its origin or manipulation: is not associated with all or a portion of a polynucleotide with which it is associated in nature; is linked to a polynucleotide other than that to which it is linked in nature; or does not occur in nature.

[00034] As used herein, the term "polypeptide" refers to a polymer of amino acids, including for example, peptides, oligopeptides, and proteins and derivatives, analogs and fragments thereof, as well as other modifications known in the art, both naturally occurring and non-naturally occurring.

[00035] As used herein, the term "pharmaceutical composition" refers to a composition containing a beneficial agent in combination with one or more pharmaceutically acceptable carriers, diluents, or excipients, and in a form suitable for administration to a human or animal.

present in the substantial absence of other biological macromolecules of the same type. The term "purified" as used herein preferably means at least 75% by weight, more preferably at least 85% by weight, more preferably still at least 95% by weight, and most preferably at least 98% by weight, of biological  
5 macromolecules of the same type present.

[00036] The term "AUC" means the area under the curve obtained from an in vivo assay in a subject by plotting blood plasma concentration of the beneficial agent in the subject against time, as measured from the time of implantation of the composition, to a time "t" after implantation. The time t will  
10 correspond to the delivery period of beneficial agent to a subject.

[00037] The term "burst index" means, with respect to a particular composition intended for systemic delivery of a beneficial agent, the quotient formed by dividing (i) the AUC calculated for the first time period after implantation of the composition into a subject divided by the number of hours  
15 in the first time period ( $t_1$ ), by (ii) the AUC calculated for the time period of delivery of beneficial agent, divided by the number of hours in the total duration of the delivery period ( $t_2$ ). For example the burst index at 24 hours is the quotient formed by dividing (i) the AUC calculated for the first twenty-four hours after implantation of the composition into a subject divided by the  
20 number 24, by (ii) the AUC calculated for the time period of delivery of beneficial agent, divided by the number of hours in the total duration of the delivery period.

[00038] The phrase "dissolved or dispersed" is intended to encompass all means of establishing a presence of beneficial agent in the gel composition  
25 and includes dissolution, dispersion, suspension and the like.

[00039] The term "systemic" means, with respect to delivery or administration of a beneficial agent to a subject, that the beneficial agent is detectable at a biologically-significant level in the blood plasma of the subject.

[00040] The term "local" means, with respect to delivery or administration of a beneficial agent to a subject, that the beneficial agent is delivered to a localized site in the subject but is not detectable at a biologically significant level in the blood plasma of the subject.

- 5 [00041] The term "gel vehicle" means the composition formed by mixture of the polymer and solvent in the absence of the beneficial agent.

[00042] The term "prolonged period" means a period of time over which release of a beneficial agent from the implant of the invention occurs, which will generally be about one week or longer, and preferably about 30 days or  
10 longer.

[00043] The term "initial burst" means, with respect to a particular composition of this invention, the quotient obtained by dividing (i) the amount by weight of beneficial agent released from the composition in a predetermined initial period of time after implantation, by (ii) the total amount  
15 of beneficial agent that is to be delivered from an implanted composition. It is understood that the initial burst may vary depending on the shape and surface area of the implant. Accordingly, the percentages and burst indices associated with initial burst described herein are intended to apply to compositions tested in a form resulting from dispensing of the composition  
20 from a standard syringe.

[00044] The term "solubility modulator" means, with respect to the beneficial agent, an agent that will alter the solubility of the beneficial agent, with reference to polymer solvent or water, from the solubility of beneficial agent in the absence of the modulator. The modulator may enhance or retard the  
25 solubility of the beneficial agent in the solvent or water. However, in the case of beneficial agents that are highly water soluble, the solubility modulator will generally be an agent that will retard the solubility of the beneficial agent in water. The solubility modulator may be a polymer, a surfactant, or a salt.

beneficial agent itself, such as by the formation of complexes, or with both. For the purposes hereof, when the solubility modulator is "associated" with the beneficial agent, all such interactions or formations as may occur are intended. Solubility modulators may be mixed with the beneficial agent prior  
5 to its combination with the viscous gel or may be added to the viscous gel prior to the addition of the beneficial agent, as appropriate.

[00045] The terms "subject" and "patient" mean, with respect to the administration of a composition of the invention, an animal or a human being.

[00046] The term "bioerodible" refers to a material that gradually  
10 decomposes, dissolves, hydrolyzes and/or erodes in situ. Generally, the "bioerodible" polymers herein are polymers that are hydrolyzable, and bioerode in situ primarily through hydrolysis.

[00047] The term "thixotropic" is used in its conventional sense to refer to a gel composition that can liquefy or at least exhibit a decrease in apparent  
15 viscosity upon application of mechanical force such as shear force. A "thixotropic agent" as used herein is one that increases the thixotropy of the composition in which it is contained, promoting shear thinning and enabling use of reduced injection force.

[00048] The polymer, solvent and other agents of the invention must be  
20 "biocompatible"; that is they must not cause irritation, inflammation or necrosis in the environment of use. The environment of use is a fluid environment and may comprise a subcutaneous or intramuscular portion or body cavity of a human or animal.

25 Injectable Depot Formulations:

[00049] As described previously, injectable depot formulations for delivery of beneficial agents over a prolonged period of time may be formed as viscous gels prior to injection of the depot into a subject. The viscous gel supports dispersed beneficial agent to provide appropriate delivery profiles,

which include those having low initial burst, of the beneficial agent as the beneficial agent is released from the depot over time.

[00050] Typically, the viscous gel will be injected from a standard hypodermic syringe that has been pre-filled with the beneficial agent-viscous gel composition as the depot. It is often preferred that injections take place using the smallest size needle (i.e., smallest diameter) to reduce discomfort to the subject when the injection takes place through the skin and into subcutaneous tissue. It is desirable to be able to inject gels through needles ranging from 16 gauge and higher, preferably 20 gauge and higher, more preferably 22 gauge and higher, even more preferably 24 gauge and higher. With highly viscous gels, i.e., gels having a viscosity of about 200 poise or greater, injection forces to dispense the gel from a syringe having a needle in the 20-30 gauge range may be so high as to make the injection difficult or reasonably impossible when done manually. At the same time, the high viscosity of the gel is desirable to maintain the integrity of the depot after injection and during the dispensing period and also facilitate desired suspension characteristics of the beneficial agent in the gel.

[00051] A thixotropic gel exhibits reduced viscosity when subjected to shear force. The extent of the reduction is in part a function of the shear rate of the gel when subjected to the shearing force. When the shearing force is removed, the viscosity of the thixotropic gel returns to a viscosity at or near that which it displayed prior to being subjected to the shearing force. Accordingly, a thixotropic gel may be subjected to a shearing force when injected from a syringe which temporarily reduces its viscosity during the injection process. When the injection process is completed, the shearing force is removed and the gel returns very near to its previous state.

[00052] A composition of a polymer and polymer solvent that includes an agent that imparts thixotropic characteristics to the viscous gel formed by the polymer solvent and polymer provides the desired advantages noted above. It is additionally desirable to use the agent in amounts that are sufficiently



small so as not to unnecessarily increase the mass and volume of the depot that is to be injected. In this regard it is desirable that the agent, i.e. lower alkanols, particularly ethanol, is not a polymer solvent. As is described more fully below, the addition of small amounts of lower alkanols, especially  
5 ethanol, to polymer depots formed as viscous gels from lactic acid-based polymers and suitable polymer solvents provide the foregoing desirable characteristics in compositions of the invention described here.

**[00053]** The polymer may be a polylactide, that is, a lactic acid-based polymer that can be based solely on lactic acid or can be a copolymer based  
10 on lactic acid and glycolic acid which may include small amounts of other comonomers that do not substantially affect the advantageous results which can be achieved in accordance with the present invention. As used herein, the term "lactic acid" includes the isomers L-lactic acid, D-lactic acid, DL-lactic acid and lactide while the term "glycolic acid" includes glycolide. The polymer  
15 may have a monomer ratio of lactic acid/glycolic acid of from about 100:0 to about 15:85, preferably from about 75:25 to about 30:70, more preferably from about 60:40 to about 40:60, and an especially useful copolymer has a monomer ratio of lactic acid/glycolic acid of about 50:50.

**[00054]** The lactic acid-based polymer has a number average molecular  
20 weight of from about 1,000 to about 120,000, preferably from about 5,000 to about 50,000, more preferably from about 8,000 to about 30,000, as determined by gel permeation chromatography (GPC). As indicated in aforementioned U.S. Patent No. 5,242,910, the polymer can be prepared in accordance with the teachings of U.S. Patent No. 4,443,340. Alternatively,  
25 the lactic acid-based polymer can be prepared directly from lactic acid or a mixture of lactic acid and glycolic acid (with or without a further comonomer) in accordance with the techniques set forth in U.S. Patent No. 5,310,865. The contents of all of these patents are incorporated by reference. Suitable lactic acid-based polymers are available commercially. For instance, 50:50 lactic  
30 acid:glycolic acid copolymers having molecular weights of 8,000, 10,000, 30,000 and 100,000 are available from Boehringer Ingelheim (Petersburg,

VA), Medisorb Technologies International L.P. (Cincinnati, OH) and Birmingham Polymers, Inc. (Birmingham, AL) as described below.

**[00055]** Examples of polymers include, but are not limited to, Poly (D,L-lactide) Resomer<sup>®</sup> L104, PLA-L104, Poly (D,L-lactide-co-glycolide) 50:50 Resomer<sup>®</sup> RG502, Poly (D,L-lactide-co-glycolide) 50:50 Resomer<sup>®</sup> RG502H, PLGA-502H, Poly (D,L-lactide-co-glycolide) 50:50 Resomer<sup>®</sup> RG503, PLGA-503, Poly (D,L-lactide-co-glycolide) 50:50 Resomer<sup>®</sup> RG506, PLGA-506, Poly (D,L-lactide-co-glycolide) 50:50 Resomer<sup>®</sup> RG755, PLGA-755, Poly L-Lactide MW 2,000 (Resomer<sup>®</sup> L 206, Resomer<sup>®</sup> L 207, Resomer<sup>®</sup> L 209, Resomer<sup>®</sup> L 214); Poly D,L Lactide (Resomer<sup>®</sup> R 104, Resomer<sup>®</sup> R 202, Resomer<sup>®</sup> R 203, Resomer<sup>®</sup> R 206, Resomer<sup>®</sup> R 207, Resomer<sup>®</sup> R 208); Poly L-Lactide-co-D,L-lactide 90:10 (Resomer<sup>®</sup> LR 209); Poly glycolide (Resomer<sup>®</sup> G 205); Poly D,L-lactide-co-glycolide 50:50 (Resomer<sup>®</sup> RG 504 H, Resomer<sup>®</sup> RG 504, Resomer<sup>®</sup> RG 505); Poly D-L-lactide-co-glycolide 75:25 (Resomer<sup>®</sup> RG 752, Resomer<sup>®</sup> RG 756); Poly D,L-lactide-co-glycolide 85:15 (Resomer<sup>®</sup> RG 858); Poly L-lactide-co-trimethylene carbonate 70:30 (Resomer<sup>®</sup> LT 706); Poly dioxanone (Resomer<sup>®</sup> X 210) (Boehringer Ingelheim Chemicals, Inc., Petersburg, VA).

**[00056]** Additional examples include, but are not limited to, DL-lactide/glycolide 100:0 (MEDISORB<sup>®</sup> Polymer 100 DL High, MEDISORB<sup>®</sup> Polymer 100 DL Low); DL-lactide/ glycolide 85/15 (MEDISORB<sup>®</sup> Polymer 8515 DL High, MEDISORB<sup>®</sup> Polymer 8515 DL Low); DL-lactide/glycolide 75/25 (MEDISORB<sup>®</sup> Polymer 7525 DL High, MEDISORB<sup>®</sup> Polymer 7525 DL Low); DL-lactide/glycolide 65/35 (MEDISORB<sup>®</sup> Polymer 6535 DL High, MEDISORB<sup>®</sup> Polymer 6535 DL Low); DL-lactide/glycolide 54/46 (MEDISORB<sup>®</sup> Polymer 5050 DL High, MEDISORB<sup>®</sup> Polymer 5050 DL Low); and DL-lactide/glycolide 54/46 (MEDISORB<sup>®</sup> Polymer 5050 DL 2A(3), MEDISORB<sup>®</sup> Polymer 5050 DL 3A(3), MEDISORB<sup>®</sup> Polymer 5050 DL 4A(3)) (Medisorb Technologies International L.P., Cincinnati, OH); and Poly D,L-lactide-co-glycolide 50:50; Poly D,L-lactide-co-glycolide 65:35; Poly D,L-lactide-co-glycolide 75:25; Poly D,L-lactide-co-glycolide 85:15; Poly DL-lactide; Poly L-lactide; Poly glycolide; Poly  $\epsilon$ -caprolactone; Poly DL-lactide-co-

caprolactone 25:75; and Poly DL-lactide-co-caprolactone 75:25 (Birmingham Polymers, Inc., Birmingham, AL).

5 [00057] The biocompatible 5 to about 90% by weight, preferably from about 10 to about 85% by weight, preferably from about 15 to about 80% by weight, preferably from about 20 to about 75% by weight, preferably from about 30 to about 70% by weight and typically from about 35 to about 65% by weight of the viscous gel, the viscous gel comprising the combined amounts of the biocompatible polymer and the solvent.

10 [00058] The solvent must be biocompatible and is selected so as to dissolve the polymer to form a viscous gel that can maintain particles of the beneficial agent dissolved or dispersed and isolated from the environment of use prior to release. Suitable solvents include lower alkyl and aralkyl esters of benzoic acid, such as benzyl benzoate, methyl benzoate, ethyl benzoate and the like, triacetin, n-methyl-2-pyrrolidone, 2-pyrrolidone, glycerol formal, methyl  
15 acetate, ethyl acetate, methyl ethyl ketone, dimethylformamide, dimethyl sulfoxide, tetrahydrofuran, caprolactam, decylmethylsulfoxide, oleic acid, and 1-dodecylazacyclo-heptan-2-one and mixtures thereof. The preferred solvents are the lower alkyl and aralkyl esters of benzoic acid, particularly benzyl benzoate and ethyl benzoate. Additional solvents are described in US  
20 Patent No. 6,130,200, which is incorporated herein by reference.

[00059] The solvent typically is present in an amount of from about 95 to about 20% by weight and is preferably present in an amount of from about 80 to about 50% by weight and often 65 to 35% by weight of the viscous gel, that is the combined amounts of the polymer and the solvent. The viscous gel  
25 formed by mixing the polymer and the solvent typically exhibits a viscosity of from about 100 to about 200,000 poise, preferably from about 500 to about 50,000 poise often from about 1,000 to about 50,000 poise measured at a 1 sec<sup>-1</sup> shear rate and 25°C using a Haake Rheometer at about 1-2 days after mixing is completed. Mixing the polymer with the solvent can be achieved

with conventional low shear equipment such as a Ross double planetary mixer for from about 1 to about 2 hours.

**[00060]** The agent that imparts thixotropic properties to the polymer gel is selected from the lower alkanols. Lower alkanol means an alcohol that  
5 contains 2-6 carbon atoms and is straight chain or branched chain. Such alcohols may be exemplified by ethanol, isopropanol, and the like. Importantly, such an agent that imparts thixotropic properties to the polymer gel is not a polymer solvent. (See e.g., Development of an in situ forming bidegradable poly-lactide-co-glycolide system for controlled release of  
10 proteins, Lambert, W.J., and Peck, K.D., Journal of Controlled Release, 33 (1995) 189-195).

**[00061]** Surprisingly, only a very small amount of agent need be added to the polymer solution of the polymer and polymer solvent to obtain the desired reduction in injection force when the gel is dispensed from a syringe.  
15 Accordingly, an amount of agent that is less than 15% by weight of the combined weight of the polymer solvent and the agent has been found to be satisfactory. The agent may be present in amounts of 0.01 to 15 weight percent, preferably in amounts of 0.1 to 5 weight percent, and often in amounts of 0.5 to 5 weight percent of the combined weight of the solvent and  
20 the agent.

**[00062]** The beneficial agent can be any physiologically or pharmacologically active substance or substances optionally in combination with pharmaceutically acceptable carriers and additional ingredients such as antioxidants, stabilizing agents, permeation enhancers, etc. that do not  
25 substantially adversely affect the advantageous results that can be attained by the present invention. The beneficial agent may be any of the agents which are known to be delivered to the body of a human or an animal and that are preferentially soluble in water rather than in the polymer-dissolving solvent. These agents include drug agents, medicaments, vitamins, nutrients,  
30 or the like. Included among the types of agents which meet this description

are nutrients, vitamins, food supplements, sex sterilants, fertility inhibitors and fertility promoters.

**[00063]** Drug agents which may be delivered by the present invention include drugs which act on the peripheral nerves, adrenergic receptors, cholinergic receptors, the skeletal muscles, the cardiovascular system, smooth muscles, the blood circulatory system, synoptic sites, neuroeffector junctional sites, endocrine and hormone systems, the immunological system, the reproductive system, the skeletal system, autacoid systems, the alimentary and excretory systems, the histamine system and the central nervous system. Suitable agents may be selected from, for example, a drug, proteins, enzymes, hormones, polynucleotides, nucleoproteins, polysaccharides, glycoproteins, lipoproteins, polypeptides, steroids, analgesics, local anesthetics, antibiotic agents, chemotherapeutic agents, immunosuppressive agents, anti-inflammatory agents including anti-inflammatory corticosteroids, antiproliferative agents, antimitotic agents, angiogenic agents, anticoagulants, fibrinolytic agents, growth factors, antibodies, ocular drugs, and metabolites, analogs (including synthetic and substituted analogs), derivatives (including aggregative conjugates/fusion with other macromolecules and covalent conjugates with unrelated chemical moieties by means known in the art) fragments, and purified, isolated, recombinant and chemically synthesized versions of these species.

**[00064]** Examples of drugs that may be delivered by the composition of the present invention include, but are not limited to, procaine, procaine hydrochloride, tetracaine, tetracaine hydrochloride, cocaine, cocaine hydrochloride, chlorprocaine, chlorprocaine hydrochloride, proparacaine, proparacaine hydrochloride, piperocaine, piperocaine hydrochloride, hexylcaine, hexylcaine hydrochloride, naepaine, naepaine hydrochloride, benzoxinate, benzoxinate hydrochloride, cyclomethylcaine, cyclomethylcaine hydrochloride, cyclomethylcaine sulfate, lidocaine, lidocaine hydrochloride, bupivacaine, bupivacaine hydrochloride, mepivacaine, mepivacaine hydrochloride, prilocaine, prilocaine hydrochloride, dibucaine and dibucaine hydrochloride, etidocaine, benzocaine, propoxycaine, dyclonin, pramoxine,

oxybuprocaine, prochlorperzine edisylate, ferrous sulfate, aminocaproic acid, mecamlamine hydrochloride, procainamide hydrochloride, amphetamine sulfate, methamphetamine hydrochloride, benzamphetamine hydrochloride, isoproterenol sulfate, phenmetrazine hydrochloride, bethanechol chloride, 5 methacholine chloride, pilocarpine hydrochloride, atropine sulfate, scopolamine bromide, isopropamide iodide, tridihexethyl chloride, phenformin hydrochloride, methylphenidate hydrochloride, theophylline choline, cephalixin hydrochloride, diphenidol, meclizine hydrochloride, prochlorperazine maleate, phenoxybenzamine, thiethylperzine maleate, 10 anisindone, diphenadione erythrityl tetranitrate, digoxin, isofluorophate, acetazolamide, methazolamide, bendroflumethiazide, chlorpromazine, tolazamide, chlormadinone acetate, phenaglycodol, allopurinol, aluminum aspirin, methotrexate, acetyl sulfisoxazole, erythromycin, hydrocortisone, hydrocorticosterone acetate, cortisone acetate, dexamethasone and its 15 derivatives such as betamethasone, triamcinolone, methyltestosterone, 17-S-estradiol, ethinyl estradiol, ethinyl estradiol 3-methyl ether, prednisolone, 17 $\alpha$ -hydroxyprogesterone acetate, 19-nor-progesterone, norgestrel, norethindrone, norethisterone, norethiaderone, progesterone, norgesterone, norethynodrel, aspirin, indomethacin, naproxen, fenoprofen, sulindac, 20 indoprofen, nitroglycerin, isosorbide dinitrate, propranolol, timolol, atenolol, alprenolol, cimetidine, clonidine, imipramine, levodopa, chlorpromazine, methyl dopa, dihydroxyphenylalanine, theophylline, calcium gluconate, ketoprofen, ibuprofen, cephalixin, erythromycin, haloperidol, zomepirac, ferrous lactate, vincamine, diazepam, phenoxybenzamine, diltiazem, 25 milrinone, mandol, quanbenz, hydrochlorothiazide, ranitidine, flurbiprofen, fenufen, fluprofen, tolmetin, alclofenac, mefenamic, flufenamic, difeninal, nimodipine, nitrendipine, nisoldipine, nicardipine, felodipine, lidoflazine, tiapamil, gallopamil, amlodipine, mioflazine, lisinopril, enalapril, enalaprilat, captopril, ramipril, famotidine, nizatidine, sucralfate, etididine, tetratolol, 30 minoxidil, chlordiazepoxide, diazepam, amitriptyline, and imipramine. Further examples are proteins and peptides which include, but are not limited to, bone morphogenic proteins, insulin, colchicine, glucagon, thyroid stimulating hormone, parathyroid and pituitary hormones, calcitonin, renin, prolactin, corticotrophin, thyrotropic hormone, follicle stimulating hormone, chorionic

gonadotropin, gonadotropin releasing hormone, bovine somatotropin, porcine somatotropin, oxytocin, vasopressin, GRF, somatostatin, lypressin, pancreozymin, luteinizing hormone, LHRH, LHRH agonists and antagonists, leuprolide, interferons such as interferon alpha-2a, interferon alpha-2b, and  
 5 consensus interferon, interleukins, growth factors such as epidermal growth factors (EGF), platelet-derived growth factors (PDGF), fibroblast growth factors (FGF), transforming growth factors- $\alpha$  (TGF- $\alpha$ ), transforming growth factors- $\beta$  (TGF- $\beta$ ), erythropoietin (EPO), insulin-like growth factor-I (IGF-I), insulin-like growth factor-II (IGF-II), interleukin-1, interleukin-2, interleukin-6,  
 10 interleukin-8, tumor necrosis factor- $\alpha$  (TNF- $\alpha$ ), tumor necrosis factor- $\beta$  (TNF- $\beta$ ), Interferon- $\alpha$  (INF- $\alpha$ ), Interferon- $\beta$  (INF- $\beta$ ), Interferon- $\gamma$  (INF- $\gamma$ ), Interferon- $\omega$  (INF- $\omega$ ), colony stimulating factors (CGF), vascular cell growth factor (VEGF), thrombopoietin (TPO), stromal cell-derived factors (SDF), placenta growth factor (PIGF), hepatocyte growth factor (HGF), granulocyte macrophage  
 15 colony stimulating factor (GM-CSF), glial-derived neurotrophin factor (GDNF), granulocyte colony stimulating factor (G-CSF), ciliary neurotropic factor (CNTF), bone morphogeneic proteins (BMP), coagulation factors, human pancreas hormone releasing factor, analogs and derivatives of these compounds, and pharmaceutically acceptable salts of these compounds, or  
 20 their analogs or derivatives.

**[00065]** In certain preferred embodiments, the beneficial agent includes chemotactic growth factors, proliferative growth factors, stimulatory growth factors, and transformational peptide growth factors including genes, precursors, post-translational-variants, metabolites, binding-proteins,  
 25 receptors, receptor agonists and antagonists of the following growth factor families: epidermal growth factors (EGFs), platelet-derived growth factor (PDGFs), insulin-like growth factors (IGFs), fibroblast-growth factors (FGFs), transforming-growth factors (TGFs), interleukins (ILs), colony-stimulating factors (CSFs, MCFs, GCSFs, GMCSFs), Interferons (IFNs), endothelial  
 30 growth factors (VEGF, EGFs), erythropoietins (EPOs), angiopoietins (ANGs), placenta-derived growth factors (PIGFs), and hypoxia induced transcriptional regulators (HIFs).

[00066] To the extent not mentioned in the previous paragraph, the beneficial agents described in aforementioned U.S. Patent No. 5,242,910 can also be used. One particular advantage of the present invention is that materials, such as proteins, as exemplified by the enzyme lysozyme, and cDNA, and DNA incorporated into vectors both viral and nonviral, which are difficult to microcapsulate or process into microspheres can be incorporated into the compositions of the present invention without the level of degradation experienced with other techniques.

[00067] The beneficial agent is preferably incorporated into the viscous gel formed from the polymer and the solvent in the form of particles typically having an average particle size of from about 0.1 to about 250 microns, preferably from about 1 to about 200 microns and often from 30 to 125 microns.

[00068] To form a suspension of particles of the beneficial agent in the viscous gel formed from the polymer and the solvent, any conventional low shear device can be used such as a Ross double planetary mixer at ambient conditions. In this manner, efficient distribution of the beneficial agent can be achieved substantially without degrading the beneficial agent.

[00069] The beneficial agent is typically dissolved or dispersed in the composition in an amount of from about 0.1% to about 50% by weight, preferably in an amount of from about 1% to about 40%, more preferably in an amount of about 2% to about 30%, and often 2 to 20% by weight of the combined amounts of the polymer, solvent, agent and beneficial agent. Depending on the amount of beneficial agent present in the composition, one can obtain different release profiles. More specifically, for a given polymer and solvent, by adjusting the amounts of these components and the amount of the beneficial agent, one can obtain a release profile that depends more on the degradation of the polymer than the diffusion of the beneficial agent from the composition or vice versa. In this respect, at lower beneficial agent loading rates, one generally obtains a release profile reflecting degradation of



the polymer wherein the release rate increases with time. At higher loading rates, one generally obtains a release profile caused by diffusion of the beneficial agent wherein the release rate decreases with time. At intermediate loading rates, one obtains combined release profiles so that if  
5 desired, a substantially constant release rate can be attained. While the particular release rate depends on the particular circumstances, such as the beneficial agent to be administered, release rates on the order of from about 0.1 micrograms/day to about 30 milligrams/day, preferably from about 1 microgram/day to about 20 milligrams per day, more preferably from about 10  
10 micrograms/day to about 10 milligram/day, for periods of from about 24 hours to about 180 days, preferably 24 hours to about 120 days, more preferably 24 hours to about 90 days, often 3 days to about 90 days can be obtained. Further, the dose of beneficial agent may be adjusted by adjusting the amount of injectable depot gel injected.

15 **[00070]** To the extent that conventional optional ingredients are desired, such as hydroscopic agents, stabilizing agents and others, they are used in an amount that does not substantially affect the advantageous results which can be attained in accordance with the present invention. Other components may be present in the gel composition, to the extent they are desired or  
20 provide useful properties to the composition, such as polyethylene glycol, hydroscopic agents, stabilizing agents (for example surfactants like tween 20, tween 80, and the like, sugars such as sucrose, trehalose, and the like, salts, antioxidants), pore forming agents, bulking agents (such as sorbitol, mannitol, glycine, and the like), chelating agents (such as divalent metal ions including  
25 zinc, magnesium, calcium, copper and the like), buffering agents (such as phosphate, acetane, succinate, histidine, TRIS, and the like) and others. When the composition includes a peptide or a protein that is soluble in or unstable in an aqueous environment, it may be highly desirable to include a solubility modulator that may, for example, be a stabilizing agent, in the  
30 composition. Various modulating agents are described in U.S. Patent Nos. 5,654,010 and 5,656,297, the disclosures of which are incorporated herein by reference. In the case of hGH, for example, it is preferable to include an amount of a salt of a divalent metal, preferably zinc. Examples of such

modulators and stabilizing agents, which may form complexes with the beneficial agent or associate to provide the stabilizing or modulated release effect, include metal cations, preferably divalent, present in the composition as magnesium carbonate, zinc carbonate, calcium carbonate, magnesium acetate, magnesium sulfate, zinc acetate, zinc sulfate, zinc chloride, magnesium chloride, magnesium oxide, magnesium hydroxide, other antacids, and the like. The amounts of such agents used will depend on the nature of the complex formed, if any, or the nature of the association between the beneficial agent and the agent. Molar ratios of solubility modulator or stabilizing agent to beneficial agent of about 100:1 to 1:1, preferably 10:1 to 1:1, typically can be utilized.

**[00071]** Pore forming agents include biocompatible materials that when contacted with body fluids dissolve, disperse or degrade to create pores or channels in the polymer matrix. Typically, organic and non-organic materials that are water soluble such as sugars (e.g., sucrose, dextrose), water soluble salts (e.g., sodium chloride, sodium phosphate, potassium chloride, and sodium carbonate), water soluble solvents such as N-methyl-2-pyrrolidone and polyethylene glycol and water soluble polymers (e.g., carboxymethylcellulose, hydroxypropyl-cellulose, and the like) can conveniently be used as pore formers. Such materials may be present in amounts varying from about 0.1% to about 100% of the weight of the polymer, but will typically be less than 50% and more typically less than 10-20% of the weight of polymer.

**[00072]** It is to be understood that the agent of the present invention does not constitute a mere diluent or a polymer-solvent that reduces viscosity by simply decreasing the concentration of the components of the composition. The use of conventional diluents can reduce viscosity, but can also cause the burst effect mentioned previously when the diluted composition is injected. In contrast, the injectable depot composition of the present invention can be formulated to avoid the burst effect by selecting the agent so that once injected into place, the agent has little impact on the release properties of the original system. Preferably, the system releases 40% or less by weight of the

beneficial agent present in the viscous gel within the first 24 hours after implantation in the subject. More preferably, 30% or less by weight of the beneficial agent will be released within the first 24 hours after implantation, and the implanted composition has a burst index of 12 or less, preferably 8 or less.

**[00073]** To further understand the various aspects of the present invention, the results set forth in the previously described Figures were obtained in accordance with the following examples.

10

#### Example 1

**[00074]** A gel vehicle for use in an injectable depot of the composition was prepared as follows. A glass vessel was tared on a Mettler PJ3000 top loader balance. Poly (D,L-lactide-co-glycolide) (PLGA), available as 50:50 Resomer<sup>®</sup> RG502 (PLGA RG 502), 50:50 Resomer<sup>®</sup> RG504 (PLGARG 504) or 50:50 DL-PLG with an inherent viscosity of 0.15 (PLGA-BPI, Birmingham Polymers, Inc., Birmingham, AL), was milled and sieved below 425 micron. The polymer was weighed into the glass vessel. The glass vessel containing the polymer was tared and the corresponding solvent was added. Amounts expressed as percentages for various polymer/solvent combinations are set forth in Table 1, below. The polymer/solvent mixture was stirred at  $250 \pm 50$  rpm (IKA electric stirrer, IKH-Werke GmbH & Co., Stanfen, Germany) for about 5 -10 minutes, resulting in a sticky paste-like substance containing polymer particles. The vessel containing the polymer/solvent mixture was sealed and placed in a temperature controlled incubator equilibrated to 37°C for 1 to 4 days, with intermittent stirring, depending on solvent and polymer type and solvent and polymer ratios. The polymer/solvent mixture was removed from the incubator when it appeared to be a clear amber homogeneous gel. Thereafter, the mixture was placed in an oven (65°C) for 30 minutes. It was noted that the PLGA-504 was dissolved in the mixture upon removal from the oven.

**[00075]** Additional depot gel vehicles are prepared with the following solvents or mixtures: benzyl benzoate ("BB"), ethanol, and propylene glycol

("PG"), and the following polymers: Poly (D,L-lactide) Resomer<sup>®</sup> L104, PLA-L104, Poly (D,L-lactide-co-glycolide) 50:50 Resomer<sup>®</sup> RG502, Poly (D,L-lactide-co-glycolide) 50:50 Resomer<sup>®</sup> RG502H, PLGA-502H, Poly (D,L-lactide-co-glycolide) 50:50 Resomer<sup>®</sup> RG503, PLGA-503, Poly L-Lactide MW 2,000 (Resomer<sup>®</sup> L 206, Resomer<sup>®</sup> L 207, Resomer<sup>®</sup> L 209, Resomer<sup>®</sup> L 214); Poly D,L Lactide (Resomer<sup>®</sup> R 104, Resomer<sup>®</sup> R 202, Resomer<sup>®</sup> R 203, Resomer<sup>®</sup> R 206, Resomer<sup>®</sup> R 207, Resomer<sup>®</sup> R 208); Poly L-Lactide-co-D,L-lactide 90:10 (Resomer<sup>®</sup> LR 209); Poly D-L-lactide-co-glycolide 75:25 (Resomer<sup>®</sup> RG 752, Resomer<sup>®</sup> RG755, Resomer<sup>®</sup> RG 756); Poly D,L-lactide-co-glycolide 85:15 (Resomer<sup>®</sup> RG 858); Poly L-lactide-co-trimethylene carbonate 70:30 (Resomer<sup>®</sup> LT 706); Poly dioxanone (Resomer<sup>®</sup> X 210) (Boehringer Ingelheim Chemicals, Inc., Petersburg, VA); DL-lactide/glycolide 100:0 (MEDISORB<sup>®</sup> Polymer 100 DL High, MEDISORB<sup>®</sup> Polymer 100 DL Low); DL-lactide/ glycolide 85/15 (MEDISORB<sup>®</sup> Polymer 8515 DL High, MEDISORB<sup>®</sup> Polymer 8515 DL Low); DL-lactide/glycolide 75/25 (MEDISORB<sup>®</sup> Polymer 7525 DL High, MEDISORB<sup>®</sup> Polymer 7525 DL Low); DL-lactide/glycolide 65/35 (MEDISORB<sup>®</sup> Polymer 6535 DL High, MEDISORB<sup>®</sup> Polymer 6535 DL Low); DL-lactide/glycolide 54/46 (MEDISORB<sup>®</sup> Polymer 5050 DL High, MEDISORB<sup>®</sup> Polymer 5050 DL Low); and DL-lactide/glycolide 54/46 (MEDISORB<sup>®</sup> Polymer 5050 DL 2A(3), MEDISORB<sup>®</sup> Polymer 5050 DL 3A(3), MEDISORB<sup>®</sup> Polymer 5050 DL 4A(3)) (Medisorb Technologies International L.P., Cincinnati, OH); and Poly D,L-lactide-co-glycolide 50:50; Poly D,L-lactide-co-glycolide 65:35; Poly D,L-lactide-co-glycolide 75:25; Poly D,L-lactide-co-glycolide 85:15; Poly DL-lactide; Poly L-lactide; Poly glycolide; Poly  $\epsilon$ -caprolactone; Poly DL-lactide-co-caprolactone 25:75; and Poly DL-lactide-co-caprolactone 75:25 (Birmingham Polymers, Inc., Birmingham, AL). Typical polymer molecular weights were in the range of 14,400 - 39,700 ( $M_w$ ) [6,400-12,200 ( $M_n$ )]. Representative gel vehicles are described in Table 1 below.

30

Table 1

Formulation	Polymer <sup>1</sup>	Benzyl Benzoate	Ethanol
-------------	----------------------	-----------------	---------

	(%)	(%)	(%)
1	50	50	0
2	50	47.5	2.5
3	50	45	5
4	50	42.5	7.5

1 = PLGA- RG502

### Example 2

#### 5 hGH Particle Preparation

[00076] Human growth hormone (hGH) particles (optionally containing zinc acetate) were prepared as follows:

hGH solution (5 mg/ml) solution in water (BresaGen Corporation, Adelaide, Australia) was concentrated to 10 mg/mL using a  
 10 Concentration/ Dialysis Selector diafiltering apparatus. The diafiltered hGH solution was washed with 5 times volume of tris or phosphate buffer solution (pH 7.6). Particles of hGH were then formed by spray drying or lyophilization using conventional techniques. Phosphate buffer solutions (5 or 50 mM) containing hGH (5 mg/mL) (and optionally various levels of zinc acetate (0 to  
 15 30 mM) when Zn complexed particles were prepared) were spray-dried using a Yamato Mini Spray dryer set at the following parameters:

Spray Dryer Parameter	Setting
Atomizing Air	2 psi
Inlet Temperature	120°C
Aspirator Dial	7.5
Solution Pump	2-4
Main Air Valve	40-45 psi

[00077] Lyophilized particles were prepared from tris buffer solutions (5 or  
 20 50 mM: pH 7.6) containing hGH (5 mg/mL) using a Durastop  $\mu$ P Lyophilizer in accordance with the following freezing and drying cycles:

Freezing cycle	Ramp down at 2.5 C/min to -30° C and hold for 30 min
	Ramp down at 2.5 C/min to -30° C and hold for 30 min
Drying cycle	Ramp up at 0.5 C/min to 10° C and hold for 960 min
	Ramp up at 0.5 C/min to 20° C and hold for 480 min
	Ramp up at 0.5 C/min to 25° C and hold for 300 min
	Ramp up at 0.5 C/min to 30° C and hold for 300 min
	Ramp up at 0.5 C/min to 5° C and hold for 5000 min

### Example 3

#### HGH-Stearic Acid Particle Preparation

- [00078]** Human growth hormone (hGH) particles were prepared as follows:
- 5 Lyophilized hGH (3.22 grams, Pharmacia-Upjohn, Stockholm, Sweden) and stearic acid (3.22 grams, 95% pure, Sigma-Aldrich Corporation, St. Louis, MO) were blended and ground. The ground material was compressed in a 13 mm round die, with a force of 10,000 pounds for 5 minutes. Compressed tablets were ground and sieved through a 70 mesh screen followed by a 400
  - 10 mesh screen to obtain particles having a size range between 38 - 212 microns.

### Example 4

#### Drug Loading

- [00079]** Compressed particulates comprising beneficial agent/stearic acid
- 15 prepared as above are added to a gel vehicle in an amount of 10 - 20 % by weight and blended manually until the dry powder is wetted completely. Then, the milky light yellow particle/gel mixture is thoroughly blended by conventional mixing using a Caframo mechanical stirrer with an attached square-tip metal spatula. Resulting formulations (6-12) are illustrated in Table
  - 20 2 below. Final homogenous gel formulations were transferred to 3, 10 or 30 cc disposable syringes for storage or dispensing.

Table 2

Formulation	Polymer <sup>1</sup> (%)	Benzyl Benzoate (%)	Ethanol (%)
5 <sup>2</sup>	45.0	45.0	0.0
6 <sup>3</sup>	40.0	40.0	0.0
7 <sup>3</sup>	45.0	44.0	1.0
8 <sup>3</sup>	39.0	39.0	2.7
9 <sup>2</sup>	39.0	39.7	0.0
10 <sup>3</sup>	31.9	47.6	0.3
11 <sup>3</sup>	33.5	44.0	0.3
12 <sup>3</sup>	40.2	36.0	0.9
13 <sup>3</sup>	32.4	44.2	1.2
14 <sup>3</sup>	32.3	44.0	1.3
15 <sup>3</sup>	36.2	39.6	1.5
16 <sup>3</sup>	32.9	40.1	1.9
17 <sup>4</sup>	35.3	45.8	0.9

1 = PLGA-502 polymer;

5

2 = 10 % particle loading (2.8% hGH, 5% stearic acid);

3 = 20 % particle loading (5% hGH, 10% stearic acid);

4 = 15 % particle loading (5% hGH, 7% stearic acid).

10 **[00080]** A representative number of implantable gels were prepared in accordance with the foregoing procedures and tested for in vitro release of beneficial agent as a function of time and also in in vivo studies in rats to determine release of the beneficial agent as determined by blood serum concentrations of beneficial agent as a function of time.

15

#### Example 5

**[00081]** Rheological behavior was tested for depot vehicles and the depot formulations formulated with different solvents prepared as described above. Formulations 1-4 were tested for viscosity under various shear rates, and viscosity was measured using a Bohlin CVO50 rheometer (Bohlin Instruments

Limited, Gloucestershire, UK) at 37°C. Figure 1 shows the viscosity of the gel formulations 1-4. Figure 2 shows the viscosity of the gel formulations 5-8. The viscosity at low shear rates represents the thickness of the gel formulation with minimal stress upon the formulation. As depicted in Figures 1 and 2, increasing the amount of ethanol in the formulation decreases the viscosity and increases shear thinning.

#### Example 6

[00082] The injection force required to dispense depot vehicles and the depot formulations was evaluated for the formulations 1-4 and 5-12, respectively. The formulations were loaded in a Hamilton 500µl Gastight® syringe (Hamilton, Reno, NV). Figure 3 is a graph illustrating the relationship between force required to inject Formulations 1-4 from a syringe using a 20 gauge needle. As shown in Figure 3, injection force of the depot vehicle formulation is significantly reduced as the amount of ethanol in the composition is increased from 0% to 15% of the combined weight of the solvent and the agent. Figures 4A & 4 B illustrate the relationship between force required to inject Formulations 9-16 from a syringe using a 24 gauge needle at 1 ml/minute, at room temperature. Notably, due to the shear thinning behavior, the formulations using ethanol as a thixotropic agent showed significantly reduced injection force while maintaining viscosities equal to or greater than the formulations using benzyl benzoate, at lower shear rate; thus maintaining the intactness of the depot after injection into the animals.

#### Example 7

##### hGH In Vivo Studies

[00083] In vivo studies in rats were performed following an open protocol to determine serum levels of hGH upon systemic administration of hGH via the implant systems of this invention. Depot gel hGH formulations were loaded into customized 0.5 cc disposable syringes. Disposable 16 gauge needles were attached to the syringes and were heated to 37°C using a circulator bath. Depot gel hGH formulations were injected into immunosuppressed rats and blood was drawn at specified time intervals. All serum samples were stored at 4°C prior to analysis. Samples were analyzed for intact hGH content using a radio immuno assay (RIA). At the end of study the rats are



euthanized for gross clinical observation and the depot was retrieved for intactness observations.

- [00084] Figures 5, 6A and 6B illustrate representative in vivo release profile of human growth hormone ("hGH") obtained in rats from various depot formulation, including those of the present invention. The in vivo release profile of the depot formulations with ethanol are comparable to the control formulations (without ethanol). Thus, the depot formulations of the present invention reduce the injection force significantly without compromising the in vivo release profile of the beneficial agent.
- 5
- 10 [00085] At the end of study (i.e. at day 28) the depots were retrieved from the rats. Generally, a one-piece intact round-shaped depot was recovered corresponding to each injected depot in the animal.
- [00086] Figures 7 and 8 show the burst index profiling the release of human growth hormone ("hGH") obtained in rats from various depot formulation, including those of the present invention. The depot formulations of the present invention significantly reduce the injection force without compromising the in vivo release profile of the beneficial agent.
- 15
- [00087] In accordance with various aspects of the present invention, one or more significant advantages can be obtained. More specifically, using simple processing steps, one can obtain a depot gel composition that can be injected into place in an animal without surgery using a low dispensing force through standard needles. Once in place, the composition will quickly return to its original viscosity and may exhibit rapid hardening so as to substantially avoid a burst effect and provide the desired beneficial agent release profile.
- 20
- 25 Furthermore, once the beneficial agent has been fully administered, there is no need to remove the composition since it is fully biodegradable. As a still further advantage, the present invention avoids the use of microparticle or microcapsulation techniques which can degrade certain beneficial agents, like peptide and nucleic acid-based drugs and which microparticles and

microcapsules maybe difficult to remove from the environment of use. Since the viscous gel is formed without the need for water, temperature extremes, or other solvents, suspended particles of beneficial agent remain dry and in their original configuration, which contributes to the stability of thereof. Further, since a mass is formed, the injectable depot gel composition may be retrieved from the environment of use if desired.

**[00088]** The invention comprises the following characteristics and features, either alone or in combination with one or more of each other:

**[00089]** a composition comprising a lactic acid-based polymer, a solvent that forms a polymer solution with said polymer, and an amount of an agent mixed with the polymer solution effective to form a thixotropic composition, said agent being selected from the group consisting essentially of lower alkanols and said amount being less than 15 weight percent of the combined weight of the solvent and the agent; the composition wherein the agent is ethanol; the composition wherein the amount of ethanol is greater than or equal to 0.01 weight percent and less than or equal to 15 weight percent of the combined weight of the solvent and the agent; the composition wherein the amount of ethanol is greater than or equal to 0.1 weight percent and less than or equal to 5 weight percent of the combined weight of the solvent and the agent; the composition wherein the amount of ethanol that is greater than or equal to 0.5 weight percent and less than or equal to 5 weight percent of the combined weight of the solvent and the agent;

**[00090]** a composition comprising polylactic acid polymer, a solvent that forms a polymer solution with said polymer, and an amount of an agent mixed with the polymer solution effective to form a thixotropic composition, said agent being selected from the group consisting essentially of lower alkanols and said amount being less than 15 weight percent of the combined weight of the solvent and the agent; the composition wherein the agent is ethanol; the composition wherein the amount of ethanol is greater than or equal to 0.01 weight percent and less than or equal to 15 weight percent of the combined

weight of the solvent and the agent; the composition wherein the amount of ethanol is greater than or equal to 0.1 weight percent and less than or equal to 5 weight percent of the combined weight of the solvent and the agent; the composition wherein the amount of ethanol that is greater than or equal to 0.5 weight percent and less than or equal to 5 weight percent of the combined weight of the solvent and the agent; the composition wherein the weight average molecular weight of the polylactic acid polymer is between about 1,000 to about 120,000; preferably about 5,000 to about 50,000; and more preferably about 8,000 to about 30,000;

- 10 **[00091]** a composition comprising a lactic acid-based polymer formed as a copolymer of lactic acid and glycolic acid, a solvent that forms a polymer solution with said polymer, and an amount of an agent mixed with the polymer solution effective to form a thixotropic composition, said agent being selected from the group consisting essentially of lower alkanols and said amount being
- 15 less than 15 weight percent of the combined weight of the solvent and the agent; the composition wherein the agent is ethanol; the composition wherein the amount of ethanol is greater than or equal to 0.01 weight percent and less than or equal to 15 weight percent of the combined weight of the solvent and the agent; the composition wherein the amount of ethanol is
- 20 greater than or equal to 0.1 weight percent and less than or equal to 5 weight percent of the combined weight of the solvent and the agent; the composition wherein the amount of ethanol that is greater than or equal to 0.5 weight percent and less than or equal to 5 weight percent of the combined weight of the solvent and the agent; the composition wherein the weight average
- 25 molecular weight of the copolymer is between about 1,000 to about 120,000; preferably about 5,000 to about 50,000; and more preferably about 8,000 to about 30,000.

**[00092]** The above-described exemplary embodiments are intended to be illustrative in all respects, rather than restrictive, of the present invention.

- 30 Thus the present invention is capable of many variations in detailed implementation that can be derived from the description contained herein by a

person skilled in the art. All such variations and modifications are considered to be within the scope and spirit of the present invention.

## WHAT IS CLAIMED IS:

1. A composition comprising a lactic acid-based polymer; a solvent that forms a polymer solution with said polymer; an amount of an agent mixed with  
5 the polymer solution effective to form a thixotropic composition, said agent being selected from the group consisting essentially of lower alkanols and said amount being less than 15 weight percent of the combined weight of the solvent and the agent; and a beneficial agent.
- 10 2. The composition of claim 1 wherein the agent is ethanol.
3. The composition of claim 2 wherein the amount of ethanol is greater than or equal to 0.01 weight percent and less than or equal to 15 weight percent of the combined weight of the solvent and the agent.
- 15 4. The composition of claim 2 wherein the amount of ethanol is greater than or equal to 0.1 weight percent and less than or equal to 5 weight percent of the combined weight of the solvent and the agent.
- 20 5. The composition of claim 2 wherein the amount of ethanol is greater than or equal to 0.5 weight percent and less than or equal to 5 weight percent of the combined weight of the solvent and the agent.
- 25 6. A composition comprising polylactic acid polymer; a solvent that forms a polymer solution with said polymer; an amount of an agent mixed with the polymer solution effective to form a thixotropic composition, said agent being selected from the group consisting essentially of lower alkanols and said amount being less than 15 weight percent of the combined weight of the solvent and the agent; a beneficial agent.
- 30 7. The composition of claim 6 wherein the agent is ethanol.

8. The composition of claim 7 wherein the amount of ethanol is greater than or equal to 0.01 weight percent and less than or equal to 15 weight percent of the combined weight of the solvent and the agent.

5 9. The composition of claim 7 wherein the amount of ethanol is greater than or equal to 0.1 weight percent and less than or equal to 5 weight percent of the combined weight of the solvent and the agent.

10. The composition of claim 7 wherein the amount of ethanol is greater than or equal to 0.5 weight percent and less than or equal to 5 weight percent of the combined weight of the solvent and the agent.

11. The composition of claim 7 wherein the weight average molecular weight in the range of about 1,000 to about 120,000.

15

12. A composition comprising a lactic acid-based polymer formed as a copolymer of lactic acid and glycolic acid; a solvent that forms a polymer solution with said polymer; an amount of an agent mixed with the polymer solution effective to form a thixotropic composition, said agent being selected

20 from the group consisting essentially of lower alkanols and said amount being less than 15 weight percent of the combined weight of the solvent and the agent; a beneficial agent.

13. The composition of claim 12 wherein the agent is ethanol.

14. The composition of claim 13 wherein the amount of ethanol is greater than or equal to 0.01 weight percent and less than or equal to 15 weight percent of the combined weight of the solvent and the agent.

30 15. The composition of claim 13 wherein the amount of ethanol is greater  
than or equal to 0.1 weight percent and less than or equal to 5 weight percent  
of the combined weight of the solvent and the agent.

16. The composition of claim 13 wherein the amount of ethanol is greater than or equal to 0.5 weight percent and less than or equal to 5 weight percent of the combined weight of the solvent and the agent.
- 5 17. The composition of claim 13 wherein the weight average molecular weight of the copolymer is between molecular weight in the range of about 1,000 to about 120,000.
- 10 18. The composition of claim 1 wherein the beneficial agent is selected from a drug, proteins, enzymes, hormones, polynucleotides, nucleoproteins, polysaccharides, glycoproteins, lipoproteins, polypeptides, steroids, analgesics, local anesthetics, antibiotic agents, chemotherapeutic agents, immunosuppressive agents, anti-inflammatory agents, antiproliferative agents, antimitotic agents, angiogenic agents, anticoagulants, fibrinolytic agents, 15 growth factors, antibodies, ocular drugs, and metabolites, analogs, derivatives, and fragments thereof.
- 20 19. The composition of claim 18 wherein the beneficial agent is present in an amount of from 0.1 to 50% by weight of the combined amounts of the polymer, the solvent and the beneficial agent.
20. The composition of claim 18 wherein the beneficial agent is in the form of particles dispersed or dissolved in the viscous gel.
- 25 21. The composition of claim 20 wherein the beneficial agent is in the form of particles wherein the particle further comprises a component selected from the group consisting of a stabilizing agent, bulking agent, chelating agent and a buffering agent.
- 30 22. The composition of claim 12 wherein the beneficial agent is selected from a drug, proteins, enzymes, hormones, polynucleotides, nucleoproteins, polysaccharides, glycoproteins, lipoproteins, polypeptides, steroids, analgesics, local anesthetics, antibiotic agents, chemotherapeutic agents, immunosuppressive agents, anti-inflammatory agents, antiproliferative agents,

antimitotic agents, angiogenic agents, anticoagulants, fibrinolytic agents, growth factors, antibodies, ocular drugs, and metabolites, analogs, derivatives, and fragments thereof.

5     23.     The composition of claim 22 wherein the beneficial agent is present in an amount of from 0.1 to 50% by weight of the combined amounts of the polymer, the solvent and the beneficial agent.

24.     The composition of claim 22 wherein the beneficial agent is in the form  
10 of particles dispersed or dissolved in the viscous gel.

25.     The composition of claim 24 wherein the beneficial agent is in the form of particles wherein the particle further comprises a component selected from the group consisting of a stabilizing agent, bulking agent, chelating agent and  
15 a buffering agent.



1/10




FIG. 1

2/10




FIG. 2

3/10

## Injection Force at 37°C (N)




FIG. 3

4/10




FIG. 4A

5/10




FIG. 4B

6/10




FIG. 5

7/10




FIG. 6A

8/10




FIG. 6B



9/10




FIG. 7

10/10




FIG. 8

## INTERNATIONAL SEARCH REPORT

Internat Application No  
PCT/US 02/36717

<b>A. CLASSIFICATION OF SUBJECT MATTER</b> IPC 7 A61K9/00 A61K47/34		
According to International Patent Classification (IPC) or to both national classification and IPC		
<b>B. FIELDS SEARCHED</b> Minimum documentation searched (classification system followed by classification symbols) IPC 7 A61K		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used) WPI Data, PAJ, CHEM ABS Data		
<b>C. DOCUMENTS CONSIDERED TO BE RELEVANT</b>		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 4 938 763 A (R.L.DUNN ET AL.) 3 July 1990 (1990-07-03) cited in the application  claims column 2, line 50 -column 4, line 2 column 4, line 44 -column 5, line 19 column 5, line 34 - line 65 column 6, line 9 - line 19 column 6, line 31 - line 41 column 6, line 55 -column 7, line 4 column 7, line 46 - line 66 column 9, line 25 - line 36 --- -/--	1,2,6,7, 11-13, 17,18, 20,22,24
<input checked="" type="checkbox"/> Further documents are listed in the continuation of box C. <input checked="" type="checkbox"/> Patent family members are listed in annex.		
* Special categories of cited documents : *A* document defining the general state of the art which is not considered to be of particular relevance *E* earlier document but published on or after the international filing date *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) *O* document referring to an oral disclosure, use, exhibition or other means *P* document published prior to the international filing date but later than the priority date claimed *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. *Z* document member of the same patent family		
Date of the actual completion of the international search  10 March 2003		Date of mailing of the international search report  17/03/2003
Name and mailing address of the ISA European Patent Office, P.B. 5618 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016		Authorized officer  Scarponi, U

# INTERNATIONAL SEARCH REPORT

Internati Application No  
PCT/US 02/36717

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 6 193 991 B1 (A.J.SHUKLA) 27 February 2001 (2001-02-27) claims figures 1,2 column 7, line 30 - line 55 ----	1-25
Y	US 6 130 200 A (K.J.BRODBECK ET AL.) 10 October 2000 (2000-10-10) cited in the application claims column 18, line 28 -column 19, line 13 ----	1-25
Y	WO 00 74650 A (ALZA) 14 December 2000 (2000-12-14) claims ----	1-25
Y	WO 99 47073 A (MERCK) 23 September 1999 (1999-09-23) claims ----	1-25
Y	US 5 674 292 A (M.M.TUCKER ET AL.) 7 October 1997 (1997-10-07) claims column 4, line 17 - line 20 column 13, line 45 - line 57 column 14, line 49 - line 64 column 15, line 8 - line 23 ----	1-25
Y	US 5 447 725 A (N.C.DAMANI ET AL.) 5 September 1995 (1995-09-05) claims ----	1-25
A,P	US 6 423 818 B1 (T. MATSUDA ET AL.) 23 July 2002 (2002-07-23) claims column 3, line 19 - line 23 column 5, line 13 - line 15 column 6, line 34 - line 37 column 6, line 54 - line 62 column 7, line 1 -column 8, line 45 examples 6,8,9 figure 1 ----	1-25
A,P	US 6 451 346 B1 (S. SHAH ET AL.) 17 September 2002 (2002-09-17) claims column 6, line 46 - line 61 column 10, line 26 - line 33 -----	1-25

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 02/36717

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4938763	A	03-07-1990	AT 151257 T 15-04-1997
			AT 228861 T 15-12-2002
			AU 644581 B2 16-12-1993
			AU 4501789 A 01-05-1990
			AU 5067793 A 17-02-1994
			BR 8907686 A 30-07-1991
			DE 68927956 D1 15-05-1997
			DE 68927956 T2 17-07-1997
			DE 68929441 D1 16-01-2003
			DK 57291 A 03-06-1991
			EP 0436667 A1 17-07-1991
			EP 0773034 A1 14-05-1997
			HK 1005012 A1 18-12-1998
			IL 91850 A 30-03-1995
			IL 107393 A 29-06-1995
			JP 2992046 B2 20-12-1999
			JP 4503163 T 11-06-1992
			KR 158669 B1 15-12-1998
			KR 158670 B1 15-12-1998
			NO 911277 A 31-05-1991
			WO 9003768 A1 19-04-1990
			US 5739176 A 14-04-1998
			US 5725491 A 10-03-1998
			US 5632727 A 27-05-1997
			US 5278201 A 11-01-1994
			US 5733950 A 31-03-1998
			US 5340849 A 23-08-1994
			US 5278202 A 11-01-1994
			US 5990194 A 23-11-1999
			ZA 8907511 A 26-06-1991
US 6193991	B1	27-02-2001	US 6432438 B1 13-08-2002
US 6130200	A	10-10-2000	US 6468961 B1 22-10-2002
			AT 203157 T 15-08-2001
			AU 5609798 A 17-07-1998
			AU 739469 B2 11-10-2001
			AU 5615498 A 17-07-1998
			DE 69705746 D1 23-08-2001
			DE 69705746 T2 31-10-2001
			DK 949905 T3 22-10-2001
			EP 0949905 A2 20-10-1999
			EP 0959873 A2 01-12-1999
			ES 2158611 T3 01-09-2001
			GR 3036599 T3 31-12-2001
			HK 1020009 A1 02-11-2001
			JP 2002512597 T 23-04-2002
			JP 2001509146 T 10-07-2001
			NZ 335851 A 23-02-2001
			PT 949905 T 28-12-2001
			WO 9827962 A2 02-07-1998
			WO 9827963 A2 02-07-1998
			US 2002034532 A1 21-03-2002
			US 6331311 B1 18-12-2001
WO 0074650	A	14-12-2000	AU 5462900 A 28-12-2000
			CZ 20014338 A3 13-03-2002
			EP 1183010 A2 06-03-2002

# INTERNATIONAL SEARCH REPORT

Information on patent family members

Internati Application No  
PCT/US 02/36717

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 0074650	A		HU 0201626 A2	28-12-2002
			JP 2003501375 T	14-01-2003
			NO 20015888 A	31-01-2002
			WO 0074650 A2	14-12-2000
WO 9947073	A	23-09-1999	AU 745841 B2	11-04-2002
			AU 3010099 A	11-10-1999
			BG 104838 A	31-07-2001
			BR 9908893 A	28-11-2000
			CA 2324265 A1	23-09-1999
			CN 1293553 T	02-05-2001
			EE 200000539 A	15-02-2002
			EP 1063942 A1	03-01-2001
			HR 20000618 A1	31-08-2001
			HU 0102385 A2	28-03-2002
			JP 2002506797 T	05-03-2002
			NO 20004616 A	15-09-2000
			PL 342858 A1	16-07-2001
			SK 13752000 A3	12-03-2001
			TR 200002685 T2	21-12-2000
			WO 9947073 A1	23-09-1999
			US 2002064547 A1	30-05-2002
US 5674292	A	07-10-1997	AT 232401 T	15-02-2003
			AU 714963 B2	13-01-2000
			AU 6333596 A	30-12-1996
			CA 2223049 A1	19-12-1996
			EP 0837701 A1	29-04-1998
			JP 11506360 T	08-06-1999
			JP 2002191686 A	09-07-2002
			WO 9640297 A1	19-12-1996
			US 6013856 A	11-01-2000
			US 6461630 B1	08-10-2002
			US 6028242 A	22-02-2000
			US 2002106394 A1	08-08-2002
US 5447725	A	05-09-1995	CA 2164933 A1	22-12-1994
			CN 1126948 A	17-07-1996
			EP 0702567 A1	27-03-1996
			JP 8511528 T	03-12-1996
			WO 9428935 A1	22-12-1994
US 6423818	B1	23-07-2002	US 2002161170 A1	31-10-2002
			US 2002169275 A1	14-11-2002
			US 2002173616 A1	21-11-2002
US 6451346	B1	17-09-2002	CA 2355657 A1	06-07-2000
			JP 2002533377 T	08-10-2002